

MASONRY

TABLE V
SANDSTONES

REF. No. (see Fig. 33).	NAME OF STONE.	SITUATION OF QUARRY.	NAME AND ADDRESS OF OWNER.	GEOLOGICAL IDENTIFICATION.		CRUSHING STRENGTH (tons per sq. ft.).	WEIGHT (lb. per cub. ft.).	CHARACTERISTICS.	POROSITY (per cent.) (see p. 99).	SATURATION COEFFICIENT (see p. 99).	RESULT OF FROST TEST (see p. 100).
				SERIES.	SYSTEM.						
30	APPLETON	Shepley, Yorkshire	Wm. Hampson & Co. Ltd., Shepley, near Huddersfield	Coal Measures	Carboniferous	686	148	Blue and brown; durable, very hard and strong; hard to work	11 (see p. 99)	0.70	Undamaged
32	APPLEY BRIDGE BLUE	Near Wigan, Lancashire	Walter Martland Ltd., Appley Bridge, near Wigan	"	"	..	152	Grey to blue; very hard and durable; fine texture; fairly easy to work	7	0.81	"
36	BERRISTALL	Pott Shrigley, Derbyshire	Ashton & Holmes Ltd., Macclesfield, Cheshire	Millstone Grit	"	278	151	Cream; durable; fine texture; free working	8	0.95	"
23	BOLTON WOODS	Near Bradford, Yorkshire	Bolton Woods Quarries Ltd., Bolton Woods, Bradford	"	"	..	148	Brownish-grey; hard and durable; fine texture	11	0.55	"
31	BRACKENHILL	Ackworth, Yorkshire	Ackworth Stone Co. Ltd., Ackworth, near Pontefract	Coal Measures	"	..	138	Light grey to brown; both fine and coarse texture; durable
25	BRAMLEY FALL	Horsforth, Leeds	A. R. Briggs & Co. Ltd., Horsforth, near Leeds	Millstone Grit	"	400	136	Grey to buff; very hard and durable; fine to coarse texture; rather difficult to work	18	0.70	Undamaged
19	BUTLER DELPH	Near Blackburn, Lancashire	John Greenwood, Railway Street, Glossop	"	"	..	163	Buff; very hard and durable; coarse grained
10	CORSEHILL, RED	Annan, Dumfriesshire, Scotland	John Murray & Sons, Annan, Dumfriesshire, Scotland	Bunter	Triassic	636	130	Pink pastel; durable; close grained; good working	21	0.60	Weathered a little at arrises
28	CROSLAND HILL	Huddersfield, Yorkshire	Crosland Hill Quarry Co. Ltd., Huddersfield	Millstone Grit	Carboniferous	573	148	Creamy-brown; very hard and durable; medium grained; good working	11	0.55	Undamaged
42	DUNGEONS	Birchover, Matlock, Derbyshire	James Akeroyd & Sons, Ltd., Birchover, Matlock, Derbyshire	"	"	612	140	Pink; very durable; fine to medium texture	15	0.66	..
17	DUNN HOUSE	Darlington, Durham	New Dunn House Quarry Co., Winston, Darlington, Co. Durham	"	"	468	135	Light brown; very durable; medium grained; very free working	15	0.66	..
7	EARNOCK	Auchentibber, High Blantyre, Scotland	Hugh B. Kerr, Station Road, Blantyre, Lanarkshire, Scotland	134	White and grey; very hard and durable; good working.	18	0.75	..
33	EDGEFOLD	Near Bolton, Lancashire	Jackson's Stone Quarries Ltd., Farnworth, Near Bolton	Coal Measures	Carboniferous	550	150	White to biscuit; very durable; fine grained; easily worked	9	0.67	Undamaged
45	ENDCLIFFE	Stanton Lees, Darley Dale, Derbyshire	Henry Deeley Ltd., Birchover, Matlock	Millstone Grit	"	612	140	Pink and brown; very durable; fine to coarse texture	15	0.67	..
24	GUISELEY	Guiseley, Leeds	A. R. Briggs & Co. Ltd., Horsforth, near Leeds	"	"	..	141	White and variegated; strong, durable; even texture; free working	15	0.70	Undamaged
13	HEWORTH BURN	Gateshead, Durham	Tate, Brown & Co., Heworth Burn and Felling Quarries, Gateshead-on-Tyne	Coal Measures	"	651	145	Bluish-grey; very hard and durable; fine grain; not easy to work	12	0.80	..
49	HOLLINGTON	Hollington and Great Gate, Stoke-on-Trent	Stanton & Bettany Ltd., Rocester, Uttoxeter, Staffordshire	Keuper	Triassic	260 (W. and S.) 289 (Red) 325 (Mottled)	133 135 138	White and salmon; very durable; fine texture; free working. Red and mottled; very durable; harder than above; free working	19	0.75	..
37	KERRIDGE	Macclesfield, Derbyshire	John Wetton & Sons Ltd., Bollington, near Macclesfield	Millstone Grit	Carboniferous	580	153	Buff; very hard and durable; fine to medium texture; good working; obtainable in large blocks	7	0.90	Undamaged