

TABLE V—SANDSTONES—Continued.

Ref. No. (see Fig. 33).	NAME OF STONE.	SITUATION OF QUARRY.	NAME AND ADDRESS OF OWNER.	GEOLOGICAL IDENTIFICATION.		CRUSHING STRENGTH (tons per sq. ft.).	WEIGHT (lb. per cub. ft.).	CHARACTERISTICS.	POROSITY (per cent.) (see p. 99).	SATURATION COEFFICIENT (see p. 99)	RESULT OF FROST TEST (see p. 100).
				SERIES.	SYSTEM.						
14	LAZONBY	Penrith, Cumberland	Henry Graves & Sons, Lazonby, Cumberland	Upper Permian	Permian	..	146	"Red" (light terra-cotta) and "White" (light yellowish-pink); very hard and durable; coarse grained; difficult to work	10	0.63	Undamaged
9	LOCHARBRIGGS	Dumfries, Scotland	Baird & Stevenson (Quarrymasters) Ltd., 11 Bothwell Street, Glasgow, C.2	Bunter	Triassic	405	125	Pale salmon pink; durable; medium texture; free working; obtainable in large blocks	25	0.70	Weathered a little at arrises
18	LONGRIDGE	Near Preston, Lancashire	Thomas Croft & Sons Ltd., Blackpool Road, Preston	Millstone Grit	Carboniferous	..	145	Grey and brown; very durable; medium-grained; excellent working	12	0.75	Undamaged
30	MIDDLEWOOD	Oughtibridge, Sheffield	Joseph Turner Ltd., Oughtibridge, Sheffield	"	"	White to snuff brown; durable; medium to coarse texture
35	RUNCORN, RED	Weston, near Runcorn, Cheshire	The Runcorn Stone Co., Weston, near Runcorn	Keuper	Triassic	254	130	Red and mottled; durable; coarse to fine texture; easily worked	21	0.65	Weathered a little at arrises
31	SCOUT STONE	Halifax, Yorkshire	B. Riley & Sons (Quarry Owners) Ltd., Halifax, Yorkshire	Millstone Grit	Carboniferous	..	172	Light brown to greyish-white; hard and durable
11	SHAWK	Thursby, near Carlisle	W. & W. Graves, 41 Chiswick Street, Carlisle	Bunter	Triassic	..	138	Red, white and flecked; very durable; fine texture; free working; very suitable for carving	18	0.68	..
12	SPRINGWELL	Gateshead, Co. Durham	Richard Kell & Co. Ltd., Springwell Quarries, near Gateshead-on-Tyne	Coal Measures	Carboniferous	..	160	Yellow; very durable; medium grained; fairly easy to work
15	ST. BEES, RED	St. Bees, Cumberland	Tom McKay & Sons Ltd., St. Bees, Cumberland	Bunter	Triassic	393	142	Bright red; very durable; fine grained; good working
46	STANCLIFFE	Stancliffe, Derbyshire	The Stancliffe Estates Co. Ltd., Darley Dale, Derbyshire	Millstone Grit	Carboniferous	646	145	Honey to very light drab; very hard and durable; uniform texture, close-grained; good working	12	0.65	..
43	STANTON PARK	Birchover, Matlock	James Akeroyd & Sons Ltd., Birchover, Matlock, Derbyshire	"	"	600	150	Pink and brown; very durable; fine to coarse texture
44	STANTON WOODHOUSE	Stanton Lees, Darley Dale, Derbyshire	Henry Deeley Ltd., Birchover, Matlock, Derbyshire	"	"	512	140	Brown; very durable; fine texture	16	0.68	..
22	THORNTON BLUE	Near Bradford, Yorkshire	C. Cockroft Ltd., Black Dyke Quarries, Thornton, Bradford	Coal Measures	"	..	148	Bluish-grey; very hard and durable; fine grained; costly to work	11	0.55	Undamaged
29	WELLFIELD	Huddersfield, Yorkshire	Samuel Johnson & Son (Mirfield) Ltd., Crosland Hill, Huddersfield	Millstone Grit	"	705	150	Brown; very durable; fine grained; free working	9	0.90	..
20	WEST END	Keighley, Yorkshire	Chas. Barrett & Sons Ltd., Oxenhope, near Keighley	"	"	..	153	Brown; very hard and durable; fine texture	8	0.93	..
38	WINDYWAY	Macclesfield, Derbyshire	John Wetton & Sons Ltd., Bollington, near Macclesfield	608	153	Bluish-grey; durable; fine to medium grained; good working; obtainable in large blocks
26	WOODKIRK BLUE	Morley, near Leeds	George Armitage & Sons Ltd., Robin Hood, Wakefield, Yorkshire	Coal Measures	Carboniferous	672	146	Blue; durable; fine grained; good working	10	0.65	..
27	WOODKIRK BROWN	"	"	"	"	515	142	Brown; durable; fine grained; good working	14	0.65	..
34	WOOLTON	Woolton, Liverpool	Morrison & Sons Ltd., Wavertree, Liverpool, 15	Bunter	Triassic	518	130	Red; durable; fine grained; good working	22	0.60	Weathered a little at arrises